

Technical Characteristics

Property	Typical Value
Binder Type	Cement-based with acrylic additives
Appearance	Fine white powder
Specific Gravity	1.3–1.4 (after mixing)
Setting/Drying Time	2–4 hours (depends on thickness & environment)
Recoat Time	After 6–8 hours (depending on drying conditions)
Coverage	0.8–1.2 m ² /kg per coat (depending on surface condition)
Mixing Ratio	Approx. 1 kg powder: 0.35–0.4 L clean water
Application Tools	Putty knife, hand trowel, scrapper

Values may vary depending on surface and environmental conditions.

Application Method

- Mix powder with clean water to form a smooth, lump-free paste.
- Apply with a putty knife or trowel in thin layers.
- Allow each coat to dry completely before applying subsequent layers.
- Sand lightly after drying to achieve a smooth surface before painting.

Cleaning

Clean tools and equipment immediately after use with water.

Storage & Shelf Life

- Store in a cool, dry place in sealed bags.
- Shelf life: 12 months from the date of manufacture.

Health & Safety

- Avoid inhalation of powder and contact with eyes.
- Use protective gloves and masks during mixing and application.
- Keep out of reach of children.
- Refer to Material Safety Data Sheet (MSDS) for detailed safety information.