

Technical Characteristics

Property	Typical Value
Binder Type	Styrene Acrylic Copolymer
Appearance	White, smooth paste
Finish	Matt
Specific Gravity	1.60–1.70
Volume Solid	50–60 %
Touch Dry Time	1–2 hours (depends on thickness & environment)
Recoat Time	After 4–6 hours (depending on drying conditions)
Coverage	2.5–3 m ² /kg per coat (depending on surface condition)
Application Tools	Putty knife, hand trowel, scrapper
Thinning	Ready-to-use; no thinning required

Values may vary depending on surface and environmental conditions.

Application Method

- Stir putty before use for uniform consistency.
- Apply in thin layers using a putty knife or trowel.
- Allow each coat to dry completely before applying subsequent coats.
- After drying, sand the surface lightly for smoothness before painting.

Cleaning

Clean tools and equipment immediately after use with water.

Storage & Shelf Life

- Store in a cool, dry place away from direct sunlight.
- Shelf life: 12 months in unopened original container.

Health & Safety

- Avoid contact with eyes and prolonged skin contact.
- Ensure adequate ventilation during application.
- Keep out of reach of children.
- Refer to Material Safety Data Sheet (MSDS) for detailed safety information.